

GRADE	4LB			
STANDARD OF TEST	Q/320412 CNW 001-2015			
DENSITY	kg/m ³	95-125	105.0	
TENSILE STRENGTH	kpa	≥ 800	1182.7	
TENSILE RATE	%	≥ 80	134	
TEARING STRENGTH	N/m	≥ 1200	2190	
COMPRESSION DEFLECTION	kpa	≥ 120	192.2	
HARDNESS	°	45-55	52	
				