

GRADE (EB-2015)				
STANDARD OF TEST Q/320412 CNW 002-2015				
DENSITY	Kg/m ³	110-170	113.2	GB/T 6343-2009
TENSILE STRENGTH	Kpa	◦ 200	572.9	GB/T 6344-2008